TECHNICAL DATA SHEET

Level*More* Absolute 30

01/01/24

Kelmore's LevelMore Absolute 30 is an ultra-rapid setting, high performance, flexible, 2 part levelling and smoothing compound which can be applied from 2mm to 20mm in a single application. Ensuring excellent adhesion, it is suitable for use on a wide range of subfloors, most without the need to prime. Its dependable moisture tolerance also enables use below damp proof membranes. Providing superb flowing capabilities and dimensional stability, this protein free product sets with an outstanding surface finish and can be walked on after just 30 minutes. Resilient floor coverings can be fitted after just 90 minutes and porcelain, ceramic, and natural stone tiles can be fixed after only 45 minutes. LevelMore Absolute 30 has been manufactured to the highest of standards using unique technologies, extensive knowledge and outstanding raw materials. When compared to the production of traditional cementitious flooring compounds, this results in a significant reduction in CO₂ emissions. Additionally, Kelmore is committed to supporting the reduction of plastic waste, and by manufacturing LevelMore Absolute 30 liquid in pouches rather than bottles, we have reduced the plastic packaging of this product by >80%.



LevelMore Absolute 30

Classificatio	CT-C16-F10		
Unit Size	Bag: 20kg Pouch: 4.5 litre		
Application (air and bac	≥ 5°C		
Application Thickness	Minimum Maximum	2mm 20mm	
@20°C	Working time Walk on Tile after Fit resilient floor coverings after	15 minutes 30 minutes 45 minutes 90 minutes	
Consumption	Approximately 1.58kg /m²		
After 28 Days	Compressive Strength Flexural Strength	16 N/mm² 10 N/mm²	

Areas of Use						
Floors	Domestic	Over Adhesive	Below Damp Proof	Water Piped Underfloor Heating	Limited Movement/	
Interior	Commercial	Residues	Membranes	Electric Underfloor Heating	Vibration	





LevelMore Absolute 30

Suitable Floor Backgrounds					PRIMER REQUIRED		
Asphalt (Flooring Grade)	Existing Cera Porcelain, an Natural Ston	nd	Plywood Overlay (Class 3)		Tile Backer Boards	None Required	
A Cement:Sand Screed (inc. Heated)** A Concrete**					Prime <i>More</i> Universal		
₿ Epoxy DPM*			B Metal (Steel)		H)	Prime <i>More</i> Grip	
© Calcium Sulphate/Anhydrite Screed (inc. Heated)					Prime <i>More</i> CS		
Prime <i>More</i> Universal un		unc	ime with one neat, ndiluted coat of ime <i>More</i> Grip.		eat,	Prime with one neat, undiluted coat of Prime <i>More</i> CS.	

The primer must be allowed to dry before applying LevelMore Absolute 30.

BACKGROUND AND SURFACE PREPARATION

Backgrounds must be sufficiently dry and strong enough to carry the total weight being applied. All surfaces must be clean, sound and free from contaminants that could inhibit adhesion, such as dust, dirt, oil, grease, laitance, and curing agents. Timber bases must be adequately ventilated and able to carry the additional static and dynamic load without deflection. Ensure any remaining adhesive residues are hard, sound, well adhered and not softened by water.

Guidance notes on suitable floor backgrounds

The following backgrounds do not require priming.

EXISTING CERAMIC, PORCELAIN, AND NATURAL STONE

TILES: Must be in good condition, free of any contaminants and well bonded. Ensure the existing structure can take the additional weight.

When fitting resilient flooring, Level*More* Absolute 30 should be applied with a minimum thickness of 3mm to provide an absorbent base for the application of adhesives. If the existing tiles are fixed to a floor that does not contain an effective structural damp proof membrane, Kelmore DPM must be applied either directly to the surface of the prepared tiles or to a pre-smoothing layer of Level*More* Absolute 30.

FLOORING GRADE ASPHALT: Must be hard, sound and firmly adhered. When fitting resilient flooring, Level*More* Absolute 30 should be applied with a minimum thickness of 3mm to provide an absorbent base for the application of adhesives.

PLYWOOD OVERLAY (CLASS 3): Ensure the subfloor is rigid, flat, dry and adequately ventilated. The plywood must be conditioned to the appropriate moisture content for the environment. When levelling or smoothing prior to fitting resilient floor coverings, the plywood overlay must be a minimum 6mm thick and screw fixed at 100mm centres around the perimeter of the sheet and 150mm centres elsewhere. When levelling or smoothing prior to tiling with porcelain, ceramic or natural stone tiles, the plywood overlay must be a minimum 15mm thick and screw fixed at a maximum 300mm centres.

TILE BACKER BOARDS: Ensure the boards are installed as instructed by the manufacturer and that they are securely fixed to suitable, rigid, prepared bases. Where the boards have been installed on solid bases using tile adhesive, ensure the adhesive has fully set before applying the product. Please note that some proprietary boards can be susceptible to point loading and will require the compound to be applied at a minimum thickness before installing some floor coverings.

ADHESIVE RESIDUES: Must be hard, sound, well bonded and not softened by water. Only apply Level*More* Absolute 30 at a thickness of 3mm to 6mm.

For best results, including improved adhesion, workability and surface finish, prime the following backgrounds with one coat of Prime*More* Universal diluted 1:3 by volume with clean water (1 part Prime*More* Universal to 3 parts clean water).

Allow the primer to dry before applying the flooring compound.

CEMENT:SAND SCREED: When levelling or smoothing prior to tiling with porcelain, ceramic or natural stone tiles, newly installed screeds should be allowed to dry for a minimum of 3 weeks. For preparation and drying times of proprietary cementitious screeds, follow the guidance of the manufacturer.

Continued on next page...

^{*}Kelmore DPM does not require priming if applying LevelMore Absolute 30 within 24 hours of application.

^{**}Although priming is not necessary for the compound to bond to these porous backgrounds, priming is recommended to regulate background porosity and will result in improved adhesion, workability and the product's surface finish.



LevelMore Absolute 30

When levelling or smoothing prior to fitting resilient floor coverings, screeds must have an effective structural damp proof membrane and be confirmed dry, no greater than 75% Relative Humidity (RH). If the screed does not contain an effective structural damp proof membrane, or residual construction moisture is present up to 98% RH, Kelmore DPM must be applied to the surface. Level*More* Absolute 30 is moisture tolerant and can be used to pre-smooth screeds before applying the DPM.

HEATED CEMENT:SAND SCREED: New heated screeds must be commissioned from 3 weeks after screed installation and before work commences. The screed should be heated slowly at a maximum rate of 5°C per day until the maximum operating temperature (as recommended by the heating manufacturer) is reached. Hold this temperature for 3 days before allowing the screed to cool. All proprietary cementitious screeds should be commissioned and prepared in accordance with the recommendations of the screed manufacturer.

When fitting resilient floor coverings, ensure the moisture content of the screed is no greater than 75% Relative Humidity (RH) before levelling or smoothing.

Underfloor heating must be switched off 48 hours prior to levelling or smoothing.

CONCRETE: When levelling or smoothing prior to tiling with porcelain, ceramic or natural stone tiles, new concrete must be given time to cure before being allowed to continuously air dry in good conditions for a minimum of 6 weeks.

When levelling or smoothing prior to fitting resilient floor coverings, the concrete must have an effective structural damp proof membrane and be confirmed dry, no greater than 75% Relative Humidity (RH). If the concrete does not contain an effective structural damp proof membrane, or residual construction moisture is present up to 98% RH, Kelmore DPM must be applied to the surface. Level*More* Absolute 30 is moisture tolerant and can be used to pre-smooth concrete before applying the DPM.

Power floated concrete should be mechanically prepared by suitable means to provide a clean, sound, micro-textured, dust free surface.

Prime the following backgrounds with one neat, undiluted coat of Prime*More* Grip. Allow the primer to dry before applying the flooring compound.

EPOXY DPM: Must be a flooring grade that is compatible with cementitious products. Ensure it is hard, sound and firmly adhered. When fitting resilient flooring, Level*More* Absolute 30 should be applied with a minimum thickness of 3mm to provide an absorbent base for the application of adhesives.

Kelmore DPM does not require priming if applying Level*More* Absolute 30 within 24 hours of application.

METAL (STEEL): Must be rigid, corrosion-free, clean and free from contaminants that could inhibit adhesion, including oil and grease. When fitting resilient flooring, Level*More*Absolute 30 should be applied with a minimum thickness of 3mm to provide an absorbent base for the application of adhesives.

Prime calcium sulphate/anhydrite screeds with one neat, undiluted coat of Prime*More* CS. Allow the primer to dry before applying the flooring compound.

CALCIUM SULPHATE/ANHYDRITE SCREEDS: All laitance and surface contaminants must be completely removed. The screed must be confirmed adequately dry, no greater than 85% Relative Humidity (RH) when levelling or smoothing prior to tiling with porcelain, ceramic or natural stone tiles, and no greater than 75% RH when levelling or smoothing prior to fitting resilient floor coverings.

HEATED CALCIUM SULPHATE/ANHYDRITE SCREEDS: All laitance and surface contaminants must be completely removed. New heated screeds must be commissioned before commencing work. This can be started from 7 days after the screed has been installed and heat should be introduced slowly and in accordance with the recommendations of the screed manufacturer. When levelling or smoothing prior to tiling with porcelain, ceramic or natural stone tiles, ensure the moisture content of the screed is no greater than 85% Relative Humidity (RH), and no greater than 75% RH when levelling or smoothing prior to fitting resilient floor coverings.

Underfloor heating must be switched off 48 hours prior to levelling or smoothing.

SPECIFIC PRODUCT INFORMATION:

- LevelMore Absolute 30 is moisture tolerant, making it suitable for use on damp subfloors providing no surface
 water is present and for use below damp proof membranes. When the product is used to pre-smooth subfloors,
 the subsequent application of Kelmore DPM will have improved coverage.
- LevelMore Absolute 30 can be used to encapsulate electric underfloor heating cables. Before the cables or mats are adhered to the floor, ensure that the background has been prepared. Where resilient floor coverings are to be fitted, LevelMore Absolute 30 must be applied at a thickness as recommended by the manufacturer to ensure the floor covering does not suffer heat damage.
- After completing installations on backgrounds incorporating underfloor heating, the heating system should not be run for 10 days. Following this period, the floor temperature must be gradually raised to its optimal operating temperature.
- LevelMore Absolute 30 can be used to smooth or level uneven timber floors prior to overlaying with plywood or tile backer boards. The timber floor must be rigid, adequately ventilated and free of all contaminants that could inhibit adhesion and be primed with one neat, undiluted coat of PrimeMore Grip. The primer must be dry before applying the compound, and the compound must be allowed a minimum of 3 hours to fully dry before fitting the sheets or boards.
- Where possible, Level*More* Absolute 30 should be applied at the desired thickness in a single application. If additional coats are required, allow the previous coat to completely dry before priming with Prime*More* Universal diluted 1:3 by volume with clean water. Additional coats must not exceed the thickness of the previous coat.
- · LevelMore Absolute 30 is protein free, making it suitable for use in biologically sensitive areas.



Level*More* Absolute 30

Mixing

Level*More* Absolute 30 is a 2 part product, Level*More* Absolute 30 powder must only be mixed with Level*More* Absolute 30 liquid at a ratio of 20kg powder to 4.5 litres of liquid.

Pour the Level*More* Absolute 30 liquid into a clean bucket. Gradually add the powder whilst mixing thoroughly with an electric paddle mixer until a smooth, lump-free consistency is achieved. The compound is ready for use immediately after mixing.

Application

Level*More* Absolute 30 can be applied at a thickness of 2mm to 20mm in a single application. Pour the mixed compound onto the prepared floor before using a trowel or rake to regulate the thickness and guide the product into the desired areas. Whilst the product is still wet, the use of a *spiked roller can further enhance the surface finish by removing any trapped air.

*The use of a spiked roller is only recommended when the product has been applied at a thickness that will allow the roller to freely roll through the compound.

Drying

Drying times will vary dependent on the porosity of the background, ambient temperature and humidity. When tested to the industry standard temperature of 20°C, Level*More* Absolute 30 can be walked on after 30 minutes. Resilient floor coverings can be fitted after 90 minutes and porcelain, ceramic, and natural stone tiles can be fixed after 45 minutes. Please be aware that higher temperatures and low humidity will shorten the drying time and lower temperatures and high humidity will extend the drying time.

Coverage

Coverage will vary dependent on the texture of the background and the application thickness of the product. As a guide, a 20kg bag of Level*More* Absolute 30 powder mixed with 4.5 litres of Level*More* Absolute 30 liquid will provide the following approximate coverage:

Application Thickness	2mm	3mm	5mm	10mm	20mm
Approximate Coverage	6.3m ²	4.2m ²	2.5m ²	1.26m ²	0.63m ²

NOTES: All cementitious flooring compounds should only be used when the temperature (air and background) is 5°C or above. If temperatures drop below 5°C then the chemical reaction required for cement to set is impeded, dramatically slowing the setting process. This will only return to normal when temperatures rise. Additionally, if the temperatures drop to below freezing before the compound has set, then the integrity and performance of the product will be compromised.

Where temperatures are in excess of 30°C, the set time of the product will be accelerated significantly, potentially making it difficult to use. When work must be undertaken in higher temperatures every effort should be made to ensure the temperature of the air, background and products are kept as cool as possible.

CLEANING: All tools should be cleaned with water after use and before the product sets.

HEALTH AND SAFETY: For detailed information, please refer to and follow the advice stated on the SDS (Safety Data Sheet) which can be accessed on our website – www.kelmore.co.uk or alternatively by contacting Kelmore Ltd.

STORAGE AND SHELF LIFE: Level*More* Absolute 30 powder and liquid must be stored in unopened packaging, off the ground, and in cool, dry conditions. If stored in this way, the shelf life of this product is 12 months.

BS 8203 & BS 5385: Level*More* Absolute 30 should be used in conjunction with work carried out under the British Codes of Practice for the Installation of Resilient Floor Coverings, or for Wall and Floor Tiling.

All the information supplied by Kelmore Ltd is offered in good faith and is derived from the company's combined knowledge, experience and testing. Without prior notice, due to on-going research and development, the information we offer can be updated at any time. Kelmore's products are developed, tested and manufactured to consistently high standards, however, we accept no liability for any loss or damage which may arise from factors outside of our control, such as site conditions and/or the execution of the work.



FN 13813[.] CT-C16-F10